

# EVlzero

## Transparent binder for conglomerates.


### Technical data sheet

Technical features	Typical values	Standard applied
Dynamic viscosity at 160°C	> 700 mPa*s	UNI EN 13702
Penetration at 25°C	25 – 55 dmm	UNI EN 1426
Softening point	> 75 °C	UNI EN 1427
Flash point	> 170 °C	DIN 51755 ASTM D92,D93
Density at 25°C	850 kg/m <sup>3</sup>	EN ISO 3838

Storing and mixing temperatures	
Storing temperature	Ambient temperature
Mixing temperature	160 – 170 °C

Product presentation	
Colour	Transparent
Shape	Chips: 10 x 10 x 3 mm approx.
Packaging	15 kg PE bags

The above data indicate average production values. Their purpose is to give general indications and they do not constitute a guarantee of certain specific properties of the product illustrated.



**EVlzero is a brand of CORECOM s.r.l.**